

ABSTRACT OF THE DISCLOSURE

B1

A filtration method for liquid metal in which the liquid metal passes through a bed of refractory particulate material formed from grains having an open porosity between 5 and 30%. Electrofused corundum may be used as the refractory particulate material. The invention enables the use of reduced retention times while maintaining a quality level at least equal to that obtained with other particulate materials.